



## Promalene EVA 2-18

COPOLYMER

Melt Index – 2 gr/ 10 min  
Vinyl Acetate - 18%

### Suggested Applications

Microcellular Crosslinked Foam.

Blends, extrusion of tubing and hoses, good clarity, toughness, and flexibility.

### Nominal Properties

<b>PROPERTY</b>	<b>TEST METHOD</b>	<b>Unit</b>	<b>Value</b>
Vinyl Acetate		%	18
Melt Index 190°C/ 2.16 kg	D1238	g/10 min.	2
Density	D792	g/cc	0.937
Ultimate Tensile Strength	D 638	MPa	25
Brittleness Temperature	D 746	C	<-85
Tensile			
Strength@break	D 638	MPa	20
Elongation@break		%	740
Hardness	D 2240	Shore A	64
Vicat Softening Point	D1525	C	64
Flexural Modulus	D 790	MPa	48
1% Secant			

Makes no representation or warranty of any kind, express or implied, with respect to this product, as to merchantability, Fitness for particular particular purpose or otherwise. The data listed represents average values and are believed to be reliable, They are given for information; no guarantee of their accuracy is made, however, and the product is sold upon condition that purchasers shall make their own test to determinate the characteristics of the product and the suitability of the product for their particular process.